

KumhoSunny PC HCG2520

Polycarbonate

Shanghai KumhoSunny Plastics Co., Ltd.

Message:

HCG2520 is 20%GF PC resin. It has high rigidity and super shape resistance property. HCG2520 is mainly used in electron & electric parts,etc.

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	High Rigidity		
Uses	Electrical Parts		
	Electrical/Electronic Applications		
UL File Number	E254819		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.32	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20 to 0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	95.0	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	6000	MPa	ASTM D790
Flexural Strength	150	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	140	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	145	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	270 to 280	°C	
Middle Temperature	280 to 290	°C	
Front Temperature	290 to 300	°C	
Nozzle Temperature	280 to 290	°C	
Processing (Melt) Temp	240 to 300	°C	

Mold Temperature	60.0 to 100	°C
Back Pressure	0.200 to 0.800	MPa
Screw Speed	20 to 80	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

