Europrene® N 3945

Acrylonitrile Butadiene Rubber

Versalis S.p.A.

Message:

Europrene® N 3945 is a cold polymerized acrylonitrile-butadiene copolymer made at the Porto Torres production facility in Italy. A non staining antioxidant is added during the production process.

The high ACN content confers to compounds based on Europrene® N 3945 good hardness properties and good oil and aliphatic hydrocarbon swelling resistance. The vulcanization can be performed using a sulphur based systems or with peroxides. The low temperature properties can be improved by adding polar plasticizers as synthetic esters of adipic, sebacic or phtalic acids. To improve heat, light and ozone resistance, suitable protective agents as amine or phenolic antioxidants have to be added in the compounding process.

Wide range of technical articles requiring good processability and a very high oil and fuel resistance.

| General Information | | | |
|----------------------------------|-----------------------|------|-------------|
| Additive | Antioxidant | | |
| Features | Antioxidant | | |
| | Fuel Resistant | | |
| | High Hardness | | |
| | Hydrocarbon Resistant | | |
| | Oil Resistant | | |
| | | | |
| Appearance | Yellow | | |
| Forms | Bale | | |
| Physical | Nominal Value | Unit | Test Method |
| Mooney Viscosity (ML 1+4, 100°C) | 45 | MU | ASTM D1646 |
| Acrylonitrile Content | 39.0 | wt% | ASTM D3533 |
| Ash Content | < 0.5 | wt% | ASTM D5667 |
| Organic Acid | < 0.5 | wt% | ASTM D5774 |
| Soap | < 0.6 | wt% | ASTM D5774 |
| Volatile Matter | < 0.70 | wt% | ASTM D5668 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

