

ESTOPLAST XU 64001NN01

Polyamide 66
Ester Industries Ltd.

Message:

Polyamide 66 - Unfilled, Flame Retardant
Automotive: Electrical components and connectors
Electrical & Electronic: Low voltage switch gear/power distribution, Lighting, Power connectors , MCB

General Information			
Additive	demoulding		
	Flame retardancy		
Features	Good demoulding performance		
	Flame retardancy		
Uses	Lighting Applications		
	Electrical/Electronic Applications		
	Connector		
	Application in Automobile Field		
Appearance	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Water Absorption			ISO 62
Saturated, 23°C	1.5	%	ISO 62
Equilibrium, 23°C, 50% RH	2.8	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	74.0	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Strength	115	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	30	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	68.0	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.5 mm)	V-2		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	85 - 90	°C	

Drying Time	3.0 - 4.0	hr
Rear Temperature	260 - 270	°C
Middle Temperature	275 - 285	°C
Nozzle Temperature	280 - 290	°C
Processing (Melt) Temp	275 - 285	°C
Mold Temperature	60 - 80	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

