

ALCOM® PC 740/1.1 CF10 GF20

Polycarbonate
ALBIS PLASTIC GmbH

Message:

ALCOM® PC 740/1.1 CF10 GF20 is a Polycarbonate (PC) product filled with 10% carbon fiber and 20% glass fiber. It is available in Asia Pacific, Europe, or North America. Applications of ALCOM® PC 740/1.1 CF10 GF20 include automotive, engineering/industrial parts and housings.

Characteristics include:

- REACH Compliant
- RoHS Compliant
- Conductive
- High Stiffness

General Information			
Filler / Reinforcement	Carbon Fiber,10% Filler by Weight		
	Glass Fiber,20% Filler by Weight		
Features	Electrically Conductive		
	High Stiffness		
Uses	Automotive Applications		
	Housings		
	Machine/Mechanical Parts		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.39	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10500	MPa	ISO 527-2
Tensile Stress (Break)	130	MPa	ISO 527-2
Tensile Strain (Break)	2.2	%	ISO 527-2
Flexural Modulus	10000	MPa	ISO 178
Flexural Stress	200	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	9.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	40	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	143	°C	ISO 75-2/A
Vicat Softening Temperature	148	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+3	ohms	IEC 60093

Injection	Nominal Value	Unit
Drying Temperature		
Circulation Dryer	100 to 120	°C
Desiccant Dryer	100 to 120	°C
Drying Time		
Circulation Dryer	4.0 to 12	hr
Desiccant Dryer	2.0 to 3.0	hr
Suggested Max Moisture	0.020	%
Processing (Melt) Temp	310 to 330	°C
Mold Temperature	80.0 to 130	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

