

Adell Polyamide AO-36

Polyamide 66

Adell Plastics, Inc.

Message:

Adell Polyamide AO-36 is a Polyamide 66 (Nylon 66) material filled with 30% glass fiber. It is available in North America. Primary attribute of Adell Polyamide AO-36: Lubricated.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Molybdenum Disulfide Lubricant		
Features	Lubricated		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.20 to 0.50	%	ASTM D955
Water Absorption (24 hr)	0.80	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	98		
R-Scale	122		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	165	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	8270	MPa	ASTM D790
Flexural Strength (Yield)	228	MPa	ASTM D790
Compressive Strength	207	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	249	°C	
1.8 MPa, Unannealed	249	°C	
Melting Temperature	254 to 266	°C	
CLTE - Flow	2.3E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	0.50	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	4.9E+14	ohms · cm	ASTM D257
Dielectric Strength	20	kV/mm	ASTM D149

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT