

# Plaslube® PA6/6 ML2 HS NAT

Polyamide 66  
Techmer Engineered Solutions

Message:

Plaslube® PA6/6 ML2 HS NAT is a Polyamide 66 (Nylon 66) product. It can be processed by injection molding and is available in North America. Characteristics include:  
Flame Rated  
Heat Stabilizer  
Lubricated  
Wear Resistant

General Information			
Additive	Heat Stabilizer		
	Molybdenum Disulfide Lubricant (2%)		
Features	Good Wear Resistance		
	Heat Stabilized		
	Low Friction		
	Lubricated		
Appearance	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.16	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.3	%	ASTM D955
Water Absorption (24 hr)	0.90	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	119		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	93.1	MPa	ASTM D638
Tensile Elongation (Break)	15	%	ASTM D638
Flexural Modulus	3380	MPa	ASTM D790
Flexural Strength	117	MPa	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Steel - Dynamic	0.31		
vs. Steel - Static	0.24		
Wear Factor	150	10 <sup>-8</sup> mm <sup>3</sup> /N·m	ASTM D3702
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	37	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	104	°C	ASTM D648
CLTE - Flow	4.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Dielectric Strength <sup>1</sup>	19	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
NOTE			
1.	Method A (Short-Time)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

