

ENVIROPLAS® ENV12-NC130

Polycarbonate

ENVIROPLAS®, Inc.

Message:

Injection Molding Grade, Flame Retardant, RoHS Compliant

NC130 = To Be Assigned 5 Digit Number Indicating Opaque Natural, Black, or Opaque Custom Color.

The ENV12 Series Products Are Available With Mold Release and/or UV Stabilizer.

Contact Enviroplas Regarding UL Recognized Versions Of This Product.

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
	Colors Available		
	Natural Color		
	Opaque		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	3.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.10 to 0.30	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	62.1	MPa	ASTM D638
Tensile Elongation (Break)	120	%	ASTM D638
Flexural Modulus	2240	MPa	ASTM D790
Flexural Strength	91.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	640	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	132	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	Internal Method		
1.50 mm	V-0		
	V-0		
3.00 mm	5VA		

Injection	Nominal Value	Unit
Drying Temperature	110	°C
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.050	%
Rear Temperature	260 to 282	°C
Middle Temperature	271 to 293	°C
Front Temperature	282 to 304	°C
Nozzle Temperature	288 to 316	°C
Mold Temperature	68.3 to 93.3	°C
Injection Rate	Moderate-Fast	
Back Pressure	0.345 to 0.689	MPa
Screw Speed	40 to 70	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

