

Kemcor MD 0898

Medium Density Polyethylene

Qenos Pty Ltd

Message:

This resin is manufactured to conform to the requirements for unrestricted food contact of AS 2070 Part 1 (1992).
This product has been designed to meet the requirements for PE 80 Type B compounds under AS 4131, and is intended to be used in pipes conforming to AS 4130.

General Information	
Features	Copolymer
	Good UV Resistance
	Good Weather Resistance
	High ESCR (Stress Crack Resist.)
	High Molecular Weight
Uses	Piping
Appearance	Black
Forms	Pellets
Processing Method	Extrusion
	Pipe Extrusion

Physical	Nominal Value	Unit	Test Method
Density	0.952	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.12	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	60		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1070	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	18.0	MPa	
Break	25.0	MPa	
Tensile Elongation (Break)	800	%	ASTM D638
Flexural Modulus	650	MPa	ASTM D790

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

