Exac PVDF

Polyvinylidene Fluoride

Saint Gobain - Norton

Message:

Exac PVDF is a Polyvinylidene Fluoride (PVDF) product. It is available in North America. Applications of Exac PVDF include engineering/industrial parts, electrical/electronic applications, aerospace, automotive and medical/healthcare.

Characteristics include:

Flame Rated

Chemical Resistant

Good Weather Resistance

Heat Resistant

Mechanical

General Information								
Features	Good Chemical Resistance Good Thermal Stability Good Weather Resistance Low Friction							
					Machinable			
					Self Lubricating			
	Uses	Aerospace Applications						
Automotive Applications								
Bearings								
Bushings								
Connectors								
Electrical Parts								
Insulation								
Medical Devices								
Pump Parts								
Seals								
Valves/Valve Parts								
Agency Ratings	ASTM D 3222							
Forms	Rod							
	Tubing							
Physical	Nominal Value	Unit	Test Method					
Specific Gravity	1.77	g/cm³	ASTM D792					
Water Absorption (24 hr)	0.050	%	ASTM D570					
Hardness	Nominal Value	Unit	Test Method					
Durometer Hardness (Shore D)	78		ASTM D2240					

Unit

Test Method

Nominal Value

Flame Rating	V-0		UL 94
Flammability	Nominal Value	Unit	Test Method
Arc Resistance	55.0	sec	ASTM D495
1 MHz	0.020		
60 Hz	0.030		
Dissipation Factor			ASTM D150
1 MHz	9.50		
60 Hz	8.50		
Dielectric Constant			ASTM D150
Dielectric Strength	11	kV/mm	ASTM D149
Volume Resistivity	2.0E+14	ohms·cm	ASTM D257
Surface Resistivity	4.0E+14	ohms	ASTM D257
Electrical	Nominal Value	Unit	Test Method
Thermal Conductivity	0.12	W/m/K	ASTM C177
CLTE - Flow	1.0E-4	cm/cm/°C	ASTM D696
Melting Temperature	155 to 170	°C	
Brittleness Temperature	-62.2	°C	ASTM D746
Continuous Use Temperature	129	°C	ASTM D794
1.8 MPa, Unannealed	87.8	°C	
0.45 MPa, Unannealed	132	°C	
Deflection Temperature Under Load			ASTM D648
Thermal	Nominal Value	Unit	Test Method
Notched Izod Impact (24°C)	210	J/m	ASTM D256
Impact	Nominal Value	Unit	Test Method
Compressive Strength	85.8	MPa	ASTM D695
Flexural Strength (Yield)	61.4	MPa	ASTM D790
Flexural Modulus	1720	МРа	ASTM D790
Tensile Elongation (Yield)	180	%	ASTM D638
Tensile Strength (Yield)	42.9	МРа	ASTM D638
Tensile Modulus	1380	MPa	ASTM D638

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

