

Andur 75-DGP-3

Polyurethane (Polyether, TDI)
Anderson Development Company

Message:

Andur 75-DGP-3 is a Polyurethane (Polyether, TDI) (PUR-Ether/TDI) product. It is available in North America.

General Information			
Features	Low Hysteresis		
Forms	Liquid		
Physical	Nominal Value	Unit	Test Method
Apparent Density	1.10	g/cm ³	ASTM D1895
Molding Shrinkage - Flow	2.0	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	74		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	43.4	MPa	ASTM D638
Tensile Elongation (Yield)	250	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	30.3	MPa	ASTM D412
Compression Set	43	%	ASTM D395
Thermoset	Nominal Value	Unit	Test Method
Pot Life (70°C)	2.0	min	
Thermoset Mix Viscosity (70°C)	1160	cP	ASTM D2393
Demold Time (100°C)	960	min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT