# Andur 2-920 AP

## Polyurethane (Polyester/Polyether mix, TDI)

### Anderson Development Company

#### Message:

Andur 2-920AP is a polyester/polyether TDI terminated coprepolymer suitable for the preparation of urethane elastomers. When cured with Curene 442 [4,4'-methylene-bis (orthochloroaniline)], an elastomer with 92 Shore A hardness will be produced. Elastomers of lower hardness can be obtained using blends of Curene 442 and polyols and other diamine curatives, or by the use of plasticizers.

General Information			
Features	Solvent resistance		
	Hydrolysis stability		
Forms	Liquid		
Thermoset	Nominal Value	Unit	Test Method
Thermoset Mix Viscosity (100°C)	370	сР	ASTM D2393
Additional Information			

NCO: 5.4 to 5.8%Viscosity, 77°F: Waxy Solid cps

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

