

Panlite® ML-3206ZT

Polycarbonate

TEIJIN LIMITED

Message:

Injection Molding grade, Light diffusion grade, Weather resistance, Flame resistance

General Information			
UL YellowCard	E50075-100078396	E244324-101516724	
Features	Low Light Diffusion		
	Good weather resistance		
	Flame retardancy		
Uses	LEDs		
	Lighting Applications		
	Illumination diffuser		
Appearance	milky white		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	18.0	cm³/10min	ISO 1133
Molding Shrinkage			Internal method
Transverse flow: 4.00mm	0.50 - 0.70	%	Internal method
Flow: 4.00mm	0.50 - 0.70	%	Internal method
Water Absorption (23°C, 24 hr)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2400	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	61.0	MPa	ISO 527-2/50
Fracture	57.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	6.0	%	ISO 527-2/50
Nominal Tensile Strain at Break	> 50	%	ISO 527-2/50
Flexural Modulus ¹	2130	MPa	ISO 178
Flexural Stress ²	95.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10	kJ/m²	ISO 179
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature (1.8 MPa, Unannealed)	127	°C	ISO 75-2/A
Linear thermal expansion coefficient			ISO 11359-2
Flow	7.0E-5	cm/cm/°C	ISO 11359-2
Lateral	7.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+13	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.0 mm	V-2		UL 94
3.0 mm	V-2		UL 94
Glow Wire Flammability Index			IEC 60695-2-12
1.0 mm	800	°C	IEC 60695-2-12
3.0 mm	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			IEC 60695-2-13
1.0 mm	850	°C	IEC 60695-2-13
3.0 mm	850	°C	IEC 60695-2-13
Optical	Nominal Value	Unit	Test Method
Transmittance (3000 μm)	77.0	%	ASTM D1003
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

