Vipel® F737-BTB-20

Polyester Alloy

AOC, L.L.C.

Message:

Vipel Resilient Isophthalic Polyester Resin

AOC's Vipel F737 series is a resilient isophthalic polyester resin with excellent mechanical properties. Vipel F737 resins are used extensively in grating and in the construction of large diameter water pipes for transporting water to and from power stations. Vipel F737 resins can be adapted for a variety of fabrication processes.

Internationally Recognized

Vipel F737 series resins have been used in many corrosion resistant applications such as grating and water pipes, etc.

Corrosion Resistance

This resin provides excellent corrosion resistance when used in contact with inorganic and organic acids. Refer to AOC's "Corrosion Resistant Resin Guide" for corrosion resistance information or for questions regarding suitability of a resin to any particular chemical environment contact AOC. Versatile

Suitable for various fabricating methods such as hand lay-up, spray-up, filament winding, etc.

Food and Drug

All resins in this datasheet are manufactured from raw materials that are listed in FDA regulation Title 21 CFR 177.2420. It is the fabricator's responsibility to also be sure that the final composite is well cured. All composites used for FDA applications should be post cured at 180°F/82°C for at least 4 hours. After post curing , laminate should be washed with soap and water and rinsed.

General Information			
Features	Acid Resistant		
	Food Contact Acceptable		
	Good Corrosion Resistance		
	Isophthalic		
	Resilient		
Uses	Coating Applications		
	Filaments		
	Piping		
Agency Ratings	FDA 21 CFR 177.2420		
Forms	Liquid		
Processing Method	Filament Winding		
	Hand Lay-up		
	Spraying		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.09	g/cm ³	
Styrene Content	43	%	
Exotherm			
Gel to Peak	8.0	min	
Peak	210	°C	
Gel Time (25°C) ¹	20.0	min	
Hardness	Nominal Value	Unit	Test Method

Barcol Hardness	39		ASTM D2583
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3380	MPa	ASTM D638
Tensile Strength (Yield)	85.5	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	3930	MPa	ASTM D790
Flexural Strength	141	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8			
MPa, Unannealed)	91.7	°C	ASTM D648
Thermoset	Nominal Value	Unit	
Thermoset Mix Viscosity ² (25°C)	350	cP	
Post Cure Time (82°C)	4.0	hr	
NOTE			
1.	Gel time with 1.1% BPO		
	Brookfield RV viscosity spindle 2 at		
2.	20 rpm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

