## Sinvicomp SIG4062

Flexible Polyvinyl Chloride

Teknor Apex Asia Pacific PTE. LTD.

## Message:

Sinvicomp SIG4062 is a Flexible Polyvinyl Chloride material. It is available in Asia Pacific for extrusion. Primary attribute of Sinvicomp SIG4062: High Stiffness.

Typical application of Sinvicomp SIG4062: Wire & Cable

| General Information                       |                           |       |             |
|---|---------------------------|-------|-------------|
| Features                                  | High Stiffness            |       |             |
| Uses                                      | Appliance Wire Insulation |       |             |
| Forms                                     | Pellets                   |       |             |
| Processing Method                         | Extrusion                 |       |             |
| Physical                                  | Nominal Value             | Unit  | Test Method |
| Specific Gravity                          | 1.50                      | g/cm³ | ASTM D792   |
| Hardness                                  | Nominal Value             | Unit  | Test Method |
| Durometer Hardness (Shore D)              | 42                        |       | ASTM D2240  |
| Mechanical                                | Nominal Value             | Unit  | Test Method |
| Tensile Strength                          | 20.0                      | МРа   | IEC 811-1-1 |
| Tensile Elongation (Break)                | 260                       | %     | IEC 811-1-1 |
| Aging                                     | Nominal Value             | Unit  | Test Method |
| Change in Tensile Strength (82°C, 168 hr) | 20                        | %     | IEC 811-1-2 |
| Change in Ultimate Elongation (82°C, 168  |                           |       |             |
| hr)                                       | 20                        | %     | IEC 811-1-2 |
| Thermal                                   | Nominal Value             |       | Test Method |
| Heat Stability <sup>1</sup> (190°C)       | 40.0                      |       | BS 2782     |
| NOTE                                      |                           |       |             |
| 1.  | Congo Red                 |       |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

