

POCAN® ECO T 3215 000000

Polybutylene Terephthalate + PET

LANXESS GmbH

Message:

PBT+PET, 15 % glass fibers, injection molding, improved surface finish, contains 30 % post consumer recyc-lat, increased temperature peak load

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Recycled Content	Yes,30%		
Features	Good Surface Finish		
	Medium Heat Resistance		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.43	g/cm ³	ISO 1183
Apparent Density	0.70	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (260°C/2.16 kg)	16.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 2577
Across Flow : 270°C, 2.00 mm ¹	1.0	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.20	%	
Flow : 270°C, 2.00 mm ³	0.50	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.10	%	
Water Absorption			ISO 62
Saturation, 23°C	0.40	%	
Equilibrium, 23°C, 50% RH	0.20	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	180	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	6000	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	110	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.0	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	5800	MPa	ISO 178/A
Flexural Stress			ISO 178/A
3.5% Strain,23°C	165	MPa	
23°C ⁶	170	MPa	
Flexural Strain at Flexural Strength ⁷ (23°C)	3.8	%	ISO 178/A
ISO Shortname	PBT+PET, GHMR, 09-060, GF15		ISO 7792
Residual Moisture Content	0.0 to 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	30	kJ/m ²	
23°C	30	kJ/m ²	
Notched Izod Impact Strength			ISO 180/1A
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Unnotched Izod Impact Strength (23°C)	25	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	190	°C	ISO 75-2/A
Vicat Softening Temperature	205	°C	ISO 306/B50
Melting Temperature ⁸	225 to 250	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow : 23 to 55°C	5.0E-5	cm/cm/°C	
Transverse : 23 to 55°C	1.1E-4	cm/cm/°C	
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
Drying Time - Circulation Dryer	4.0 to 8.0	hr	
Processing (Melt) Temp	260 to 280	°C	
Mold Temperature	80.0 to 100	°C	
NOTE			
1.	60x60x2mm, 90°C MT, 600 bar		
2.	60x60x2mm		
3.	60x60x2mm, 90°C MT, 600 bar		
4.	60x60x2mm		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	2 mm/min		
8.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

