

BUPLen® 6631

Polypropylene Homopolymer

LUKOIL Bulgaria Ltd.

Message:

The polypropylene is granulated, stabilized normally and in natural appearance.

For the production of home appliances, medical devices, technical products, packaging products for the food industry, rough textile, parts for the electrical industry and so on.

General Information			
Additive	Unspecified Stabilizer		
Features	Good Stability		
	Homopolymer		
Uses	Appliances		
	Electrical Parts		
	Engineering Parts		
	Food Packaging		
	Medical/Healthcare Applications		
	Textile Applications		
Appearance	Natural Color		
Forms	Granules		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.899 to 0.906	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) ¹ (230°C/2.16 kg)	1.0 to 3.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ²	> 30.0	MPa	ASTM D638
Flexural Modulus - 1% Secant	> 1100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	> 30	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	> 55.0	°C	ASTM D648
NOTE			
1.	Procedure A		
2.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

