

EPLAMID 66 IMP NC A801

Polyamide 66

EPSAN Plastik SAN. ve TiC. A.S.

Message:

Unreinforced and modified polyamide 66, with improved impact resistance, heat stabilized, lubricated for injection molding.

Eplamid 66 IMP A801 is used in all sectors of industry , offering a good Impact resistance .

This product is available in natural and in colours on request.

General Information				
Additive		heat stabilizer		
		Lubricant		
Features		Impact resistance, good		
		Thermal Stability		
		Lubrication		
Appearance		Available colors		
		Natural color		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.08	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Vertical flow direction: 3.00mm	1.8	--	%	ISO 294-4
Flow direction: 3.00mm	1.6	--	%	ISO 294-4
Moisture Content	0.20	--	%	ISO 15512
Hardness	Dry	Conditioned	Unit	Test Method
Durometer Hardness (Shore D, 23°C)	78	--		ISO 868
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	2300	1950	MPa	ISO 527-2/50
Tensile Stress (Break, 23°C)	48.0	42.0	MPa	ISO 527-2/50
Tensile Strain (Break, 23°C)	> 40	> 20	%	ISO 527-2/50
Flexural Modulus ¹ (23°C)	2000	1850	MPa	ISO 178
Flexural Stress ² (23°C)	85.0	75.0	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	18	20	kJ/m ²	ISO 179/1eA
Notched Izod Impact (23°C)	16	18	kJ/m ²	ISO 180/1A
Thermal	Dry	Conditioned	Unit	Test Method

Melting Temperature (DSC)	248	--	°C	ISO 3146
Flammability	Dry	Conditioned		Test Method
Flame Rating (1.60 mm)	HB	--		UL 94, IEC 60695-11-10, -20
Additional Information				
干燥				
TEST CONDITIONS: Laboratory conditions are 23 ±2°C and 45-55 % RH.				
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	2.0 - 4.0		hr	
Processing (Melt) Temp	280		°C	
NOTE				
1.	2.0 mm/min			
2.	2.0 mm/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT