Xuchuan A-8060/B-6018

Thermoplastic Polyurethane Elastomer (Polyester)

Xuchuan Chemical (Suzhou) Co., Ltd

Message:

Xuchuan A-8060/B-6018 is a Thermoplastic Polyurethane Elastomer (Polyester) (TPU-Polyester) product. It is available in Asia Pacific. Typical application: Consumer Goods.

Characteristics include:

Good Aesthetics

Low Temperature Resistant

General Information			
Features	Good Surface Finish		
	Low Temperature Resistant		
	Medium Density		
	Medium Hardness		
Uses	Footwear	Footwear	
Physical	Nominal Value	Unit	
Density	0.400 to 0.550	g/cm³	
Density			
A-8060 : 40°C	1.010 to 1.020	g/cm³	
B-6018 : 40°C	1.080 to 1.200	g/cm³	
Viscosity			
A-8060 : 40°C	1.00 to 1.40	Pa·s	
B-6018 : 40°C	0.600 to 0.800	Pa·s	
DIN Abrasion	130 to 200	mm³	
Ross Flex (-10°C) ¹	No Crack		
Cream Time	6.0 to 8.0	sec	
End of Rise Time	30.0 to 40.0	sec	
Free Rise Foam Density	200 to 260	kg/m³	
Preheat Temperature			
Part A	50 to 60	°C	
Part B	50 to 60	°C	
Preheat Time			
Part A	8.0 to 10.0	hr	
Part B	6.0 to 8.0	hr	
Processing Temperature			
Part A	40 to 45	°C	
Part B	38 to 42	°C	
Hardness	Nominal Value	Unit	
Durometer Hardness (Shore C)	60 to 85		

Elastomers	Nominal Value	Unit	
Tensile Strength (Break)	3.00 to 6.50	MPa	
Tensile Elongation (Break)	450 to 640	%	
Tear Strength	15.0 to 25.0	kN/m	
Thermoset	Nominal Value	Unit	
Thermoset Components			
Part A	Mix Ratio by Weight: 100		
Part B	Mix Ratio by Weight: 65 to 67		
Demold Time	5.0 to 7.0	min	
Injection	Nominal Value	Unit	
Mold Temperature	45.0 to 55.0	°C	
NOTE			
1.	100000 cycles		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

