

Braskem PE IA-59 U3

High Density Polyethylene

Braskem

Message:

IA59U3 is a High Density Polyethylene, narrow molecular weight homopolymer, produced by solution process for injection moulding applications. It offers high stiffness and impact strength, combined with good processability and low warpage. It contains light stabilizer and antioxidant additive.

Application:
Crates, cases, containers, pails, pallets and technical articles which require high weathering resistance.

General Information			
Additive	Antioxidant		
	UV Stabilizer		
Features	Antioxidant		
	Food Contact Acceptable		
	Good Impact Resistance		
	Good Processability		
	Good UV Resistance		
	Good Weather Resistance		
	High Stiffness		
	Homopolymer		
	Low Warpage		
	Narrow Molecular Weight Distribution		
Uses	Containers		
	Crates		
	Engineering Parts		
	Pails		
	Pallets		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.960	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	7.3	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance			ASTM D1693
50°C, 2.00 mm, 10% Igepal, Compression Molded, F50	< 3.00	hr	
50°C, 2.00 mm, 100% Igepal, Compression Molded, F50	< 3.00	hr	

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, Compression Molded)	58		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, Compression Molded	28.0	MPa	
Break, Compression Molded	25.0	MPa	
Flexural Modulus - 1% Secant (Compression Molded)	1300	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Compression Molded)	73	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, Compression Molded)	81.0	°C	ASTM D648
Vicat Softening Temperature	129	°C	ASTM D1525 ¹
Injection	Nominal Value	Unit	
Processing (Melt) Temp	160 to 230	°C	
NOTE			
1.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

