

Detectaseal® XN7H

Acrylonitrile Butadiene Rubber
Precision Polymer Engineering Ltd.

Message:

Detectaseal® is the latest advance in contamination detection and containment. This unique range of metal detectable elastomer compounds has been developed specifically to meet the stringent demands of the pharmaceutical and food processing industries.

Detectaseal® fragments as small as 2-3mm can be easily identified by in-line metal detection equipment used to detect product contaminated by process lines.

The Detectaseal® range includes Nitrile, EPDM, Silicone and Fluoropolymer (FKM) elastomer compounds (all FDA-compliant) available in blue and black, which allows the most appropriate material to be selected for every application.

Detectaseal® compounds can be moulded into O-rings and custom components.

Key Attributes

- Early detection and containment of contamination: Reduced product loss, Increased productivity
- Blue seals to assist in easy identification
- Excellent mechanical properties and sealing efficiency
- Exceptional water and steam resistance
- FDA-compliant material suitable for dry food contact applications
- Free from animal-derived ingredients

Typical Applications

- Static and dynamic sealing applications
- Food processing equipment
- Pharmaceutical drug manufacturing equipment
- Bioscience industry

General Information			
Features	Steam resistance		
	Compliance of Food Exposure		
	No kinetic components		
	Low or no water absorption		
Uses	Non-specific food applications		
	Seals		
	Drug		
Agency Ratings	FDA Food Exposure, Not Rated		
Appearance	Black		
	Blue		

Hardness	Nominal Value		Test Method
IRHD Hardness	70		ASTM D1415, ISO 48
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	10.0	MPa	ASTM D412, ISO 37
Tensile Elongation (Break)	250	%	ASTM D412, ISO 37
Compression Set			ASTM D395, ISO 815
70°C, 24 hr	30	%	ASTM D395, ISO 815
100°C, 24 hr	36	%	ASTM D395, ISO 815

Thermal	Nominal Value	Unit
Maximum Operating Temperature	120	°C
Additional Information		
Minimum Operating Temperature: -40°C (-40°F)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

