

SUMIMAC® ECR-9125K

Epoxy; Epoxide

SBHPP

Message:

One component liquid epoxy resin

Application : Ceramic filter

Advantage : Low temp. curing

General Information			
Appearance	Black		
Forms	Liquid		
Physical	Nominal Value	Unit	
Water absorption rate-Boiling water, 2 hrs soaking	0.6	wt%	
Adhesion Strength - Al/Al	8.00	MPa	
Mechanical	Nominal Value	Unit	
Flexural Modulus (25°C)	4000	MPa	
Flexural Strength (25°C)	88.0	MPa	
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	125	°C	TMA
CLTE - Flow	5.0E-5	cm/cm/°C	TMA
Uncured Properties	Nominal Value	Unit	
Density (25°C)	1.30	g/cm ³	
Viscosity (25°C)	18	Pa·s	
Curing Time			
100°C	0.50	hr	
80°C	1.0	hr	
Cured Properties	Nominal Value	Unit	
Shore Hardness (Shore D)	88		
Volume Resistivity (25°C)	1.0E+16	ohms·cm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT