

# LubriOne™ LB6600-5010 BK

Polyamide 66  
PolyOne Corporation

Message:

LubriOne™ LB6600-5010 BK is a Polyamide 66 (Nylon 66) product. It is available in Europe. Applications of LubriOne™ LB6600-5010 BK include engineering/industrial parts, appliances, automotive, business/office goods and consumer goods.

Characteristics include:

- Chemical Resistant
- Good Processability
- Medium Viscosity
- Wear Resistant

General Information			
Features	Good Chemical Resistance		
	Good Processing Stability		
	Good Wear Resistance		
	Low Friction		
	Lubricated		
	Medium Viscosity		
Uses	Appliance Components		
	Automotive Applications		
	Bearings		
	Business Equipment		
	Consumer Applications		
	Conveyor Parts		
	Gears		
	Industrial Applications		
	Printer Parts		
	Rollers		
Appearance	Black		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density <sup>1</sup> (23°C)	1.17	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage			ISO 294-4
Flow	1.1 to 1.4	%	
Across Flow : 23°C, 2.00 mm <sup>2</sup>	1.0 to 1.2	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	3400	MPa	ISO 527-2/1
Tensile Stress (23°C, 4.00 mm)	76.0	MPa	ISO 527-2/50
Tensile Strain (Break, 23°C, 4.00 mm)	> 10	%	ISO 527-2/50

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	2.8	kJ/m <sup>2</sup>	
23°C	> 3.0	kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179
-30°C	64	kJ/m <sup>2</sup>	
23°C	> 91	kJ/m <sup>2</sup>	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	232	°C	ISO 75-2/B
1.8 MPa, Unannealed	75.0	°C	ISO 75-2/A
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	270 to 300	°C	
Mold Temperature	60.0 to 90.0	°C	
NOTE			
1.	±0.02		
2.	Bergmann method		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

