RTP 2201.3 HF

Polyetheretherketone

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue' The data for this material has not been recently verified.

Please contact RTP Company for current information prior to specifying this grade.

General Information			
Filler / Reinforcement	Glass Fiber,13% Filler by Weight		
Features	High Flow		
RoHS Compliance	Contact Manufacturer		
Appearance	Black		
	Natural Color		
-	D. II		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm³	ASTM D792
Molding Shrinkage - Flow (3.18 mm, Injection Molded)	0.30 to 0.50	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.17	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (Injection Molded)	8270	МРа	ASTM D638
Tensile Strength	127	MPa	ASTM D638
Tensile Elongation (Yield, Injection			
Molded)	2.0	%	ASTM D638
Flexural Modulus (Injection Molded)	5510	МРа	ASTM D790
Flexural Strength (Injection Molded)	193	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm, Injection Molded)	48	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	450	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, Injection Molded)	232	°C	ASTM D648
Injection	Nominal Value	Unit	
Rear Temperature	343 to 388	°C	
Middle Temperature	343 to 388	°C	
Front Temperature	343 to 388	°C	
Mold Temperature	163 to 218	°C	
Injection Pressure	83.0 to 124	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

