SABIC® FORTIFY™ C13060D

Thermoplastic Polyolefin Elastomer

Saudi Basic Industries Corporation (SABIC)

Message:

SABIC® FORTIFY™ C13060D is an ethylene octene copolymer produced by solution polymerization using metallocene catalyst. This product is available as free flowing pellets.

SABIC® FORTIFY™ C13060D is designed as a low density and high performance copolymer modifier to provide superior impact properties and flow characteristics.

Typical applications are impact modifier in thermoplastic olefin compounds, footwear midsoles and wire and cable extrusion.

Please take notice of specific storage and handling conditions.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

| General Information | | | | | |
|--|-----------------------------|-------------|----------------------------------|--|--|
| Features | Low density | | | | |
| | Copolymer | | | | |
| | Impact resistance, good | | | | |
| | Good liquidity | | | | |
| | Octene comonomer | | | | |
| | | | | | |
| Uses | Wire and cable applications | | | | |
| | Composite | | | | |
| | Plastic modification | | | | |
| | Footwear | | | | |
| | | | | | |
| Forms | Particle | | | | |
| Processing Method | Wire & Cable Extrusion | | | | |
| | Compound extrusion | | | | |
| | | | | | |
| Physical | Nominal Value | Unit | Test Method | | |
| Density | 0.863 | g/cm³ | ASTM D1505 | | |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 | | | | | |
| kg) | 13 | g/10 min | ASTM D1238 | | |
| Mooney Viscosity (ML 1+4, 121°C) | 3 | MU | ASTM D1646 | | |
| Hardness | Nominal Value | Unit | Test Method | | |
| Durometer Hardness | | | ASTM D2240 | | |
| Shaw A, 1 sec | | | ASTM D2240 | | |
| | 63 | | ASTIVI DZZ40 | | |
| Shaw D, 1 sec | 16 | | ASTM D2240 | | |
| | | Unit | | | |
| Shaw D, 1 sec | 16 | Unit MPa | ASTM D2240 | | |
| Shaw D, 1 sec Mechanical | 16 Nominal Value | | ASTM D2240 Test Method | | |
| Shaw D, 1 sec Mechanical Tensile Modulus - 100% Secant | 16 Nominal Value 1.80 | МРа | ASTM D2240 Test Method ASTM D638 | | |

| Elastomers | Nominal Value | Unit | Test Method | | |
|--|---------------|------|-----------------|--|--|
| Tear Strength ¹ | 25.5 | kN/m | ASTM D624 | | |
| Thermal | Nominal Value | Unit | Test Method | | |
| Glass Transition Temperature | -56.0 | °C | Internal method | | |
| Melting Temperature | 42.0 | °C | Internal method | | |
| Additional Information | | | | | |
| All physical properties were measured on compression molded specimens. | | | | | |
| NOTE | | | | | |
| 1 | C mould | | | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

