

AIE PP 8010HMS-TFHI

Polypropylene

Asia International Enterprise (Hong Kong) Limited

Message:

Materials Features:

It is suitable for hot-plate welding. It has high melt flow strength and high sag resistance. It can be made into products of semi-transparent, low temperature resistance, impact resistance materials for automotive, motorcycle carbon canister housings, automotive expansion tank, accumulator case, power battery cases and other parts that require for hot-plate welding.

General Information			
Features	Impact resistance, good		
	High liquidity		
	Low temperature resistance		
Uses	Battery box		
	Application in Automobile Field		
	Water tank		
	Shell		
Processing Method	Blow molding		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	0.910	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	1.5	%	ASTM D955
Transverse flow	1.7	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ²	23.0	MPa	ASTM D638
Tensile Elongation ³ (Break)	> 160	%	ASTM D638
Flexural Modulus ⁴	700	MPa	ASTM D790
Flexural Strength ⁵	27.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact	500	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	74.0	°C	ASTM D648
Melting Temperature	170	°C	DSC
CLTE - Flow (-20 to 150°C)	5.5E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (23°C)	> 1.0E+15	ohms · cm	IEC 60093


Dielectric Constant (1 MHz)	3.10		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.6 mm)	HB		UL 94
NOTE			
1.	23°C		
2.	50 mm/min		
3.	50 mm/min		
4.	3.0 mm/min		
5.	3.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT