Thermoset Plastics SC-104

Silicone

Thermoset, Lord Chemical Products

Message:

Thermoset Plastics SC-104 is a Silicone material. It is available in North America for casting or encapsulating. Important attributes of Thermoset Plastics SC-104 are:

Flame Rated

Conductive

Insulating

Typical application of Thermoset Plastics SC-104: Wire & Cable

General Information					
UL YellowCard	E84716-251647				
Features	Electrically Insulating				
	Thermally Conductive				
Uses	Electronic Insulation				
Appearance	Grey				
Forms	Pellets				
Processing Method	Casting				
	Encapsulating				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	2.09	g/cm³	ASTM D792		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A)	67		ASTM D2240		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Yield)	3.31	MPa	ASTM D638		
Tensile Elongation (Yield)	120	%	ASTM D638		
Thermal	Nominal Value	Unit	Test Method		
Thermal Conductivity	0.85	W/m/K	ASTM C177		
Electrical	Nominal Value	Unit	Test Method		
Volume Resistivity	2.2E+15	ohms·cm	ASTM D257		
Dielectric Constant			ASTM D150		
100 Hz	3.10				
100 kHz	3.06				
Dissipation Factor			ASTM D150		
100 Hz	7.5E-3				
100 kHz	1.8E-3				
Flammability	Nominal Value	Unit	Test Method		
Flame Rating	V-0		UL 94		
Thermoset	Nominal Value	Unit	Test Method		

Thermoset Components				
Hardener	Mix Ratio by Weight: 1.0			
Resin	Mix Ratio by Weight: 1.0			
Thermoset Mix Viscosity (25°C)	7000	сР	ASTM D2393	
Demold Time (25°C)	1400	min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

