

# SAXALAC™ 120U

Acrylonitrile Butadiene Styrene

SAX Polymers

Message:

Saxalac 120U is an UV protected easy flowing ABS injection molding grade, characterized by high impact strength, high stiffness and good resistance to heat distortion.

| General Information                                                          |                        |                        |                 |
|------------------------------------------------------------------------------|------------------------|------------------------|-----------------|
| Additive                                                                     | UV Stabilizer          |                        |                 |
| Features                                                                     | Good Flow              |                        |                 |
|                                                                              | High Impact Resistance |                        |                 |
|                                                                              | High Stiffness         |                        |                 |
| RoHS Compliance                                                              | RoHS Compliant         |                        |                 |
| Processing Method                                                            | Injection Molding      |                        |                 |
| Physical                                                                     | Nominal Value          | Unit                   | Test Method     |
| Density                                                                      | 1.04                   | g/cm <sup>3</sup>      | ISO 1183        |
| Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)                                  | 20.0                   | cm <sup>3</sup> /10min | ISO 1133        |
| Molding Shrinkage                                                            | 0.40 to 0.70           | %                      | ISO 294-4       |
| Moisture Content <sup>1</sup>                                                | < 0.20                 | %                      | Internal Method |
| Mechanical                                                                   | Nominal Value          | Unit                   | Test Method     |
| Tensile Modulus (23°C)                                                       | 2300                   | MPa                    | ISO 527-2       |
| Tensile Stress (Break, 23°C)                                                 | 48.0                   | MPa                    | ISO 527-2       |
| Tensile Strain (Break, 23°C)                                                 | 7.0                    | %                      | ISO 527-2       |
| Impact                                                                       | Nominal Value          | Unit                   | Test Method     |
| Charpy Notched Impact Strength                                               |                        |                        | ISO 179/1eA     |
| -30°C                                                                        | 7.0                    | kJ/m <sup>2</sup>      |                 |
| 23°C                                                                         | 22                     | kJ/m <sup>2</sup>      |                 |
| Charpy Unnotched Impact Strength                                             |                        |                        | ISO 179/1eU     |
| -30°C                                                                        | 65                     | kJ/m <sup>2</sup>      |                 |
| 23°C                                                                         | 100                    | kJ/m <sup>2</sup>      |                 |
| Notched Izod Impact Strength                                                 |                        |                        | ISO 180/1A      |
| -30°C                                                                        | 7.0                    | kJ/m <sup>2</sup>      |                 |
| 23°C                                                                         | 27                     | kJ/m <sup>2</sup>      |                 |
| Unnotched Izod Impact Strength                                               |                        |                        | ISO 180         |
| -30°C                                                                        | 70                     | kJ/m <sup>2</sup>      |                 |
| 23°C                                                                         | 100                    | kJ/m <sup>2</sup>      |                 |
| Thermal                                                                      | Nominal Value          | Unit                   | Test Method     |
| Heat Deflection Temperature <sup>2</sup> (1.8 MPa, Unannealed, 60.0 mm Span) | 85.0                   | °C                     | ISO 75-2/A      |

|                                    |               |      |                |
|------------------------------------|---------------|------|----------------|
| Vicat Softening Temperature        | 99.0          | °C   | ISO 306/B50    |
| Ball Pressure Test (96°C, 2.00 mm) | Pass          |      | IEC 60335-1    |
| Flammability                       | Nominal Value | Unit | Test Method    |
| Glow Wire Flammability Index       | 650           | °C   | IEC 60695-2-12 |
| Injection                          | Nominal Value | Unit |                |
| Drying Temperature                 | 80.0          | °C   |                |
| Drying Time                        | 2.0 to 4.0    | hr   |                |
| Processing (Melt) Temp             | 220 to 260    | °C   |                |
| Mold Temperature                   | 60.0 to 90.0  | °C   |                |
| NOTE                               |               |      |                |
| 1.                                 | B130          |      |                |
| 2.                                 | 80*10*4mm     |      |                |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

