

ALCOM® PA66 910/1 GF30 PTFE20

Polyamide 66
ALBIS PLASTIC GmbH

Message:

ALCOM® PA66 910/1 GF30 PTFE20 is a Polyamide 66 (Nylon 66) product filled with 30% glass fiber. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America. Applications of ALCOM® PA66 910/1 GF30 PTFE20 include engineering/industrial parts and automotive.

Characteristics include:

- REACH Compliant
- RoHS Compliant
- Heat Stabilizer
- Lubricated
- Wear Resistant

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Heat Stabilizer		
	PTFE Lubricant (20%)		
Features	Good Wear Resistance		
	Heat Stabilized		
Uses	Automotive Applications		
	Bearings		
	Machine/Mechanical Parts		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.50	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9600	MPa	ISO 527-2
Tensile Strain (Break)	2.0	%	ISO 527-2
Flexural Modulus	9700	MPa	ISO 178
Flexural Stress	190	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	6.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	42	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	245	°C	ISO 75-2/A
Vicat Softening Temperature	240	°C	ISO 306/B50

Injection	Nominal Value	Unit
Drying Temperature	80.0	°C
Drying Time	2.0 to 12	hr
Processing (Melt) Temp	280 to 300	°C
Mold Temperature	80.0 to 120	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

