

TAROMID B 280 Z4

Polyamide 6

Taro Plast S.p.A.

Message:

Polyamide 6 elastomer modified, very high impact resistance also at low temperature, high viscosity, very good chemical resistance to oils, solvents and other chemical substances.
Available: different colours, release agent (W), and UV-stabilised (L).

General Information			
Additive	Mold Release		
	Unspecified Additive		
	UV Stabilizer		
Features	Good Chemical Resistance		
	Good Mold Release		
	Good UV Resistance		
	High Viscosity		
	Low Temperature Impact Resistance		
	Oil Resistant		
	Solvent Resistant		
	Ultra High Impact Resistance		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06 to 1.08	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage - Flow	1.2 to 1.5	%	ASTM D955
Water Absorption			
23°C, 24 hr	0.60	%	ASTM D570, ISO 62
Saturation	5.5	%	ASTM D570
Saturation, 23°C	5.5	%	ISO 62
Granule Humidity	< 0.15	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2000	MPa	ASTM D638, ISO 527-2
Tensile Strength			ASTM D638, ISO 527-2
Yield	55.0	MPa	
Break	50.0	MPa	
Tensile Elongation (Break)	> 150	%	ASTM D638, ISO 527-2

Flexural Modulus	1850	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ¹ (23°C)	85	kJ/m ²	ASTM D256, ISO 179
Notched Izod Impact (23°C, 3.20 mm)	800	J/m	ISO 180, ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	60.0	°C	ASTM D648, ISO 75-2/A
Vicat Softening Temperature	150	°C	ISO 306/B50, ASTM D1525 2
Ball Pressure Test (125°C)	Pass		VDE 0470
Melting Temperature	220	°C	ASTM D211, ISO 121
CLTE - Flow (-30 to 30°C)	7.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	3.0E+15	ohms·cm	ASTM D257
Comparative Tracking Index (Solution A)	> 600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.970 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature			
--	80.0 to 90.0	°C	
Pre-heater	80.0 to 100	°C	
Drying Time			
--	1.0	hr	
Pre-heater	3.0	hr	
Processing (Melt) Temp	230 to 270	°C	
Mold Temperature	70.0 to 80.0	°C	
Injection Rate	Fast		
NOTE			
1.	6x4x50 mm		
2.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT