

Braskem PP TR3015WV2

Polypropylene Random Copolymer

Braskem America Inc.

Message:

Nucleated, antistatic, very good mold release

Applications

Suggested uses include extrusion, blow molding

General Information	
Additive	Nucleating agent Antistatic property
Features	Nucleated Antistatic property Good demoulding performance
Agency Ratings	FDA 21 CFR 177.1520
Processing Method	Blow molding Extrusion

Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.5	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	27.6	MPa	ASTM D638
Tensile Elongation ² (Yield)	12	%	ASTM D638
Flexural Modulus - 1% Secant ³	965	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	110	J/m	ASTM D256A

NOTE	
1.	51 mm/min
2.	51 mm/min
3.	1.3 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

