

# Mediprene® 500300M

Styrene Ethylene Butylene Styrene Block Copolymer  
ELASTO

Message:

Mediprene thermoplastic elastomers are suitable for a wide variety of uses in the medical and pharmaceutical market and new applications are being developed all the time. Mediprene compounds combine the performance of vulcanised rubbers with the processing properties of thermoplastics, delivering sophisticated design opportunities through a wide and flexible range of products. Thermal and mechanical properties can be designed into the formulations and Mediprene compounds are fully recyclable and thus fulfil environmental requirements. Mediprene thermoplastic elastomers have proven to be strong alternatives as replacement for PVC. They are completely synthetic and latex free thereby minimizing allergy risks. The right TPE formulation is the key to a safe and successful medical product. When a standard formulation does not meet the needs of a unique application, we will apply our expertise in formulating a custom solution.

General Information	
Features	Good Chemical Resistance
	Good Weather Resistance
Uses	Medical/Healthcare Applications
Agency Ratings	USP Class VI
Appearance	Translucent
Forms	Pellets
Processing Method	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.890	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/5.0 kg)	18	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	30		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
--	5.00	MPa	
100% Strain	0.600	MPa	
300% Strain	1.00	MPa	
Tensile Elongation (Break)	> 800	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	15.0	kN/m	ASTM D624

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

