MIPELON™ XM-220

Ultra High Molecular Weight Polyethylene

Mitsui Chemicals America, Inc.

Message:

MIPELON™ Fine Particle Ultra High Molecular Weight Polyethylene Powder (UHMWPE Powder)

General Information			
Features	Low friction coefficient		
	Impact resistance, good		
	Dispersible		
	Good wear resistance		
	Good chemical resistance		
	Heat resistance, high		
	Self-lubricating		
Uses	Composite		
	Mixing		
	Filter material		
Forms	Powder		
Processing Method	Composite		
Physical	Nominal Value	Unit	Test Method
Density	0.940	g/cm³	ASTM D1505
Apparent Density	0.40	g/cm³	ASTM D1895
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	65		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	44.0	MPa	ASTM D638
Tensile Elongation (Break)	350	%	ASTM D638
Coefficient of Friction	0.20		ASTM D1894
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	136	°C	DSC
Additional Information			

Molecular Weight, ASTM D4020: 200E4Average particle size, Coal tar counter method: 30 µmParticle size distribution, Coal tar counter method:~20µm: 1020 to 30µm: 3530 to 40µm: 3540µm ~: 20The value listed at Melting Point DSC, was tested in accordance with ASTM D2117.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

