RTP 1500-30D

Thermoplastic Elastomer, Ether-Ester

RTP Company

Message:

RTP 1500-30D is a thermoplastic elastomer, ether-ester (TEE) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is injection molding.

| General Information | | | |
|------------------------------------|----------------------|-------|-------------|
| RoHS Compliance | Contact manufacturer | | |
| Processing Method | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.07 | g/cm³ | ASTM D792 |
| Molding Shrinkage - Flow (3.20 mm) | 0.50 - 2.0 | % | ASTM D955 |
| Moisture Content | | % | |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore D) | 30 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | 24.1 | МРа | ASTM D638 |
| Tensile Elongation (Yield) | 600 | % | ASTM D638 |
| Flexural Modulus | 27.6 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (3.20 mm) | No Break | | ASTM D256 |
| Injection | Nominal Value | Unit | |
| Drying Temperature | 98.9 | °C | |
| Drying Time | 2.0 - 3.0 | hr | |
| Processing (Melt) Temp | 191 - 210 | °C | |
| Mold Temperature | 21.1 - 48.9 | °C | |
| Injection Pressure | 68.9 - 103 | MPa | |

Desiccant Type Dryer Required.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

