

SUPRENE® 537-2

Ethylene Propylene Diene Terpolymer

SK Global Chemical

Message:

SUPRENE EPDM 537-2 is used by blending with IIR.

SUPRENE EPDM 537-2 shows excellent heat aging properties, especially with peroxide cures. It blends easily in all formulation and gives excellent weathering and low temperature impact properties.

SUPRENE EPDM 537-2 is mainly used in blends with IIR for inner tubes. It can also be used in various applications such as mechanical goods.

General Information			
Features	Good Heat Aging Resistance		
	Good Weather Resistance		
	Low Temperature Impact Resistance		
Uses	Blending		
	Machine/Mechanical Parts		
	Tubing		
Forms	Bale		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.860	g/cm ³	ASTM D792
Mooney Viscosity (ML 1+4, 125°C)	40	MU	ASTM D1646
Ethylene Content	57.0	wt%	ASTM D3900
Ethylidene Norbornene (ENB) Content	3.0	wt%	ASTM D6047
Volatile Matter	0.30	wt%	ASTM D5668

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

