

# Manner Flexible PVC 6914

Flexible Polyvinyl Chloride

Manner Plastics, L.P.

## Message:

Recommended Applications: 80°C Non-Lead Heat Stabilized Extrusion Compound for SAE J1128 types GPT, TWP, HDT.

General Information			
Additive	Heat Stabilizer		
Features	Heat Stabilized		
	Low (to None) Lead Content		
Uses	Wire & Cable Applications		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.29 to 1.33	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	37 to 43		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	19.3	MPa	ASTM D638
Tensile Elongation (Break)	300	%	ASTM D638
Additional Information	Nominal Value	Unit	
Stock Temperature - Recommended Extrusion	191	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

