

Ultra Low Outgassing™ SCV1-2596

Silicone

NuSil Technology

Message:

Controlled Volatility (CV) Silicone Materials

Silicone's ability to remain elastic at low temperatures and resistant to breakdown at high temperatures offer excellent utility in extraterrestrial environments where materials are repeatedly exposed to extreme temperatures. NuSil's Controlled Volatility (CV) and Ultra Low Outgassing TM (SCV) silicone products are used by leading space programs to provide the much-needed resilient protection they require against contamination and material degradation.

Benefits of Silicone Materials for Space

Broad Operating Temperature

Compensation for CTE Mismatch

Protection Against Atomic Oxygen

Optically Clear Formulations

Flight Legacy

Comments: Electrically Conductive, 0.005 ohm-cm, 1.2 W/m-K

General Information			
Features	Electrically Conductive		
	Low to No Outgassing		
Uses	Aerospace Applications		
	Electrical/Electronic Applications		
Agency Ratings	ASTM E 595		
	NASA SP-R-0022A		
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	2.2E-4	cm/cm/°C	
Thermal Conductivity	1.2	W/m/K	ASTM E1530
Thermoset	Nominal Value	Unit	
Thermoset Components			
Part A	Mix Ratio by Weight: 20		
Part B	Mix Ratio by Weight: 1.0		
Additional Information	Nominal Value	Unit	
Cure System	Platinum		
Uncured Properties	Nominal Value	Unit	
Color	Tan		
Density	3.41	g/cm³	
Curing Time (150°C)	0.50	hr	
Pot Life	150	min	
Cured Properties	Nominal Value	Unit	
Shore Hardness (Shore A)	85		
Tensile Strength	3.10	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

