

WPP PP PPC3225

Polypropylene Copolymer
Washington Penn Plastic Co. Inc.

Message:

WPP PP PPC3225 is a polypropylene copolymer (PP Copoly) product. It is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: automotive industry.
Features include:
Copolymer
Good stiffness
Impact resistance

General Information			
Features	Rigid, good		
	Copolymer		
	Impact resistance, good		
	Medium liquidity		
Uses	Application in Automobile Field		
	Car interior equipment		
Appearance	Available colors		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.898	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	70		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	22.0	MPa	ASTM D638
Flexural Modulus - Tangent ²	1000	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	120	J/m	ASTM D256
Injection	Nominal Value	Unit	
Drying Temperature	71.1 - 87.8	°C	
Drying Time	1.0	hr	
Rear Temperature	204 - 210	°C	
Middle Temperature	210 - 216	°C	
Front Temperature	216 - 221	°C	
Nozzle Temperature	221 - 227	°C	
Mold Temperature	15.6 - 48.9	°C	
Injection Pressure	4.14 - 7.58	MPa	

Holding Pressure	1.03 - 4.14	MPa
Back Pressure	0.517 - 1.03	MPa
Clamp Tonnage	3.4 - 5.5	kN/cm ²
Cushion	3.18 - 6.35	mm

Injection instructions

Injection Speed: 1.5 to 2.5 in/sZone 4 Temperature: 420 to 430°FHot Runner Temperature: 410 to 440°FHydraulic Oil Temperature: 110 to 125°FShot Capacity vs. Barrel Capacity: 2.5 to 4Screw Decompression: 0.1 to 0.25 in

NOTE

1. 50 mm/min
2. 1.3 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

