

Exxtral™ Performance Polyolefin HMU234

Polypropylene, Compounded (TPO)

ExxonMobil Chemical

Message:

A special thermoplastic polyolefin black resin with high rigidity, high thermal stability, low emission and low odor performance is suitable for automotive HVAC and parts under the hood.

General Information			
Features	Good dimensional stability		
	Low volatilization		
	Rigidity, high		
Uses	Parts under the hood of a car		
	Application in Automobile Field		
	Car interior parts		
Appearance	Black		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.07	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	12.0	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - Secant	3200	MPa	ISO 527-2
Tensile Stress (Yield)	34.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	4.0	%	ISO 527-2/50
Flexural Modulus	3450	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C, Complete Break)	3.4	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	64.0	°C	ISO 75-2/A
Additional Information			
Unless otherwise specified herein: data were prepared pursuant to ExxonMobil's sampling and testing procedures in effect at time of production; and applicable sampling and testing methods are available upon request. Values may result from interpolation or correlation of other data.Sampling and testing methods are subject to change without notice unless otherwise agreed in writing.			
Legal statement			
本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用本产品不宜在与食品接触的应用中使用.			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

