

BCC Resins DP-11-75

Polyurethane

BCC Products Inc.

Message:

DP-11-75 is a two component medium viscosity urethane patch system. A hybrid product which was designed specifically for making quick responsive repairs/buildups to the MB 4000 Foundry Plank. DP-11-75 is exceptionally tough, highly machinable after cure, and exhibits superior properties similar to MB 4000.

General Information				
Features	Good Toughness			
	Machinable			
	Medium Viscosity			
Uses	Repairing Material			
Appearance	Red			
Forms	Liquid			
Thermoset	Nominal Value	Unit	Test Method	
Thermoset Components				
Part A	Mix Ratio by Volume: 1.0			
Part B	Mix Ratio by Volume: 1.0			
Pot Life ¹ (25°C)	1.5	min	ASTM D2393	
Thermoset Mix Viscosity				
25°C ²	1600	cP		
25°C ³	200	cP		
Post Cure Time	0.33 to 0.50	hr		
NOTE				
1.	20 gr. mass			
2.	Brookfield, Part B			
3.	Brookfield, Part A			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT