TEKALOY™ S630XB

Polycarbonate + PBT

Mando Advanced Materials Co., Ltd.

Message:

TEKALOY[™] S630XB is a Polycarbonate + PBT (PC+PBT) product. It is available in Asia Pacific. Characteristics include: Good Weather Resistance Heat Stabilizer

General Information					
Additive	Heat Stabilizer				
Features	Good Weather Resistance				
	Heat Stabilized				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.21	g/cm³	ASTM D792		
Molding Shrinkage ¹			ASTM D955		
Flow	0.60	%			
Across Flow	0.60	%			
Mechanical	Nominal Value	Unit	Test Method		

Across Flow	0.60	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	68.6	MPa	ASTM D638
Tensile Elongation (Break)	90	%	ASTM D638
Flexural Modulus	2400	MPa	ASTM D790
Flexural Strength	88.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	200	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load	ASTM D648		
0.45 MPa, Unannealed	113	°C	
1.8 MPa, Unannealed	105	°C	
Injection	Nominal Value	Unit	
Processing (Melt) Temp	260 to 280	°C	
Mold Temperature	60.0 to 80.0	°C	
NOTE			
1	60°C Mold Temperature		

1.

60°C Mold Temperature

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

