

# Trilene FreeFlow™ 67

Ethylene Propylene Copolymer

Lion Copolymer, LLC

## Message:

A Free-Flowing Ethylene-Propylene-Ethylidene Norbornene Low Molecular Weight Polymer on Silicon Dioxide

Trilene FreeFlow 67 is a free-flowing polymer made by combining Trilene liquid polymer and silica. The blend is nominally 68% ethylene-propylene copolymer and 32% silica. It is available as a dry, free-flowing powder that is easy to measure, store, and transfer. It incorporates quickly and thoroughly into various elastomer systems, and gives quality and processing advantages when compared to neat polymer. Trilene FreeFlow 67 is effective in EPDM, BR, NR, SBR and other elastomers.

General Information		
Filler / Reinforcement	Silica gel filler, 32% filler by weight	
Features	Low molecular weight	
	Workability, good	
Uses	Mixing	
Appearance	White	
	brownish yellow	
Forms	Powder	
Physical	Nominal Value	Unit
Specific Gravity	1.05	g/cm <sup>3</sup>
Ethylidene Norbornene (ENB) Content	9.5	wt%
Molecular weight-Viscosity Average	7000	
Volatile Matter (100°C)		%
Additional Information		
Ethylene/Propylene: 45/55		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT