

DOW™ LLDPE 6200

Linear Low Density Polyethylene Resin

The Dow Chemical Company

Message:

DOW™ LLDPE 6200 is a Linear Low Density Polyethylene Resin material. It is available in Latin America.

Typical application of DOW™ LLDPE 6200: Food Contact Applications

General Information			
Agency Ratings	EU No 10/2011		
	FDA 21 CFR 177.1520(c) 3.2a		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.927	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	20	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (50°C, 100% Igepal)	130	hr	ASTM D1693
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	13.0	MPa	
Break	9.00	MPa	
Tensile Elongation (Break)	250	%	ASTM D638
Flexural Modulus - 2% Secant	314	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	No Break		ASTM D256
Injection	Nominal Value	Unit	
Processing (Melt) Temp	190 to 230	°C	
Mold Temperature	5.00 to 30.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT