# **APEX® 1835**

### Flexible Polyvinyl Chloride

#### Teknor Apex Company

#### Message:

APEX® 1835 is a flexible polyvinyl chloride material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is injection molding. APEX® The main features of the 1835 are: ROHS certification Good flexibility Heat resistance Typical application areas include: Wire and cable engineering/industrial accessories Electrical/electronic applications

General Information				
Features	Flexibility at low temperatures			
	Heat resistance, high			
Uses	Plug			
	Washer			
	Connector			
	Fatigue elimination supplies			
Wire Types	Molded member			
RoHS Compliance	RoHS compliance			
Appearance	Opacity			
Forms	Particle			
Processing Method	Injection molding	Injection molding		
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.29	g/cm³	ASTM D792	
Molding Shrinkage - Flow	1.5 - 1.8	%	ASTM D955	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A, 15 sec)	70		ASTM D2240	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	11.0	MPa	ASTM D638	
Tensile Elongation (Break)	400	%	ASTM D638	
Thermal	Nominal Value	Unit	Test Method	
Continuous Use Temperature	105	°C	ASTM D794	
Brittleness Temperature	-43.0	°C	ASTM D746	
Flammability	Nominal Value	Unit	Test Method	
Oxygen Index	25	%	ASTM D2863	
Additional Information				

温度额定值:105℃			
Injection	Nominal Value	Unit	
Processing (Melt) Temp	174	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

