Pearlbond[™] 522

Thermoplastic Polyurethane Elastomer (Polycaprolactone)

Lubrizol Advanced Materials, Inc.

Message:

Pearlbond © 522 is a linear, polycaprolactone-copolyester polyurethane, supplied in form of white spherical granules with a very high crystallization rate and a very high thermoplasticity level.

Pearlbond ® 522 can be added to formulations of REACTIVE POLYURETHANE HOT-MELTS (HMPUR), in order to improve the crystallisation speed.

| General Information | | | |
|---------------------------------------|-----------------------|----------|-----------------|
| Features | Crystalline | | |
| | Solvent Resistant | | |
| | | | |
| Uses | Plastics Modification | | |
| Agency Ratings | EC 1907/2006 (REACH) | | |
| Appearance | White | | |
| Forms | Granules | | |
| Physical | Nominal Value | Unit | Test Method |
| Density (20°C) | 1.19 | g/cm³ | ISO 2781 |
| Melt Mass-Flow Rate (MFR) (170°C/21.6 | | | |
| kg) | 110 to 160 | g/10 min | ISO 1133 |
| Moisture Content | < 1500 | ppm | Internal Method |
| Crystallization Rate | 9.0 to 11.0 | min | Internal Method |
| OH Value | < 3.00 | mg KOH/g | Internal Method |
| Thermoplasticity | Very High | | Internal Method |
| Thermal | Nominal Value | Unit | Test Method |
| Melting Temperature | 65.0 to 69.0 | °C | Internal Method |
| Fill Analysis | Nominal Value | Unit | Test Method |
| Melt Viscosity (130°C) | 4900 | Pa·s | ISO 1133 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

