

Huafon JF-P-8060 / JF-I-6008 (General outsole)

Polyurethane (Polyester based)

Huafon Group Co., Ltd.

Message:

Characteristics: High hardness.

Applications: For man/woman shoes and wood-like shoes.

| General Information | | |
|-----------------------------|-------------------------------|-------------------|
| Additive | Unspecified Additive | |
| Features | High Hardness | |
| Uses | Footwear | |
| Forms | Liquid | |
| Physical | Nominal Value | Unit |
| Density ¹ | 0.400 to 0.450 | g/cm ³ |
| Hardness | Nominal Value | Unit |
| Hardness | | |
| Asker A : 23°C | 55.0 to 65.0 | |
| Asker C : 23°C | 73.0 to 83.0 | |
| Thermoset | Nominal Value | Unit |
| Thermoset Components | | |
| Part A | Mix Ratio by Weight: 100 | |
| Part B | Mix Ratio by Weight: 82 to 88 | |
| Uncured Properties | Nominal Value | Unit |
| Color ² | Clear/Transparent | |
| Density | | |
| 40°C ³ | 1.14 to 1.18 | g/cm ³ |
| 40°C ⁴ | 1.18 to 1.20 | g/cm ³ |
| Viscosity | | |
| 40°C ⁵ | 0.060 to 0.18 | Pa·s |
| 40°C ⁶ | 1.0 to 1.6 | Pa·s |
| Cured Properties | Nominal Value | Unit |
| Tensile Strength | > 4.00 | MPa |
| Tensile Elongation at Break | > 200 | % |
| Tear Strength | > 20.0 | kN/m |
| NOTE | | |
| 1. | Molded Density | |
| 2. | Part B | |
| 3. | Part A | |
| 4. | Part B | |
| 5. | Part B | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

