

# AMTOPP WM18

Polypropylene  
Inteplast Group

Message:

Solid White Metallized CoEx  
BIAXIALLY ORIENTED POLYPROPYLENE FILM ONE SIDE SEALABLE FOR FOOD PACKAGING

General Information			
Uses	Film		
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	17	μm	
Tensile Strength			ASTM D882
MD : Yield	138	MPa	
TD : Yield	221	MPa	
Tensile Elongation			ASTM D882
MD : Break	140	%	
TD : Break	60	%	
Oxygen Transmission Rate (22°C, 0% RH)	47	cm³/m²/24 hr	ASTM D3985
Water Vapor Transmission Rate (38°C, 90% RH)	0.31	g/m²/24 hr	ASTM F1249
Yield <sup>1</sup>	62.3	m²/kg	
Optical Density	2.5	%	Internal Method
Heat Seal Temperature <sup>2</sup>	93	°C	
NOTE			
1.	Internal Method		
2.	1/2 sec, 30 PSI		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT