

Shin-Etsu Elastomer KE-2001-50A/B

Silicone Rubber, HTV

Shin-Etsu Silicones of America

Message:

Shin-Etsu Elastomer KE-2001-50A/B is a Silicone Rubber, HTV material. This product is available in North America.

General Information		
Features	Fast curing	
Physical	Nominal Value	Unit
Specific Gravity	1.14	g/cm ³
Hardness	Nominal Value	Unit
Durometer Hardness	53	
Elastomers	Nominal Value	Unit
Tensile Stress (100% Strain)	1.74	MPa
Tensile Strength	9.90	MPa
Tensile Elongation (Break)	590	%
Tear Strength ¹	39.9	kN/m
Compression Set (180°C, 22 hr)	5.0	%
Thermoset	Nominal Value	Unit
Post Cure Time (200°C)	4.0	hr
Additional Information		
Press Cure / Post Cure: Press/Post		
Uncured Properties	Nominal Value	Unit
Curing Time	0.083	hr
NOTE		
1.	B mould	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT