

# Hostacom TRC 333N D72643

Polypropylene

LyondellBasell Industries

## Message:

Hostacom TRC 333N is a 20% mineral filled PP compound. Excellent scratch resistance, very low stress whitening and low emissions. High flow, good stiffness/impact balance. High UV-resistance for use in interior trim applications.

General Information			
Filler / Reinforcement	Mineral,20% Filler by Weight		
Features	Good Impact Resistance		
	Good Stiffness		
	Good UV Resistance		
	High Flow		
	Low Emissions		
	Scratch Resistant		
Uses	Automotive Applications		
	Automotive Interior Trim		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	18	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	21.0	MPa	ISO 527-2/50
Tensile Strain (Break)	75	%	ISO 527-2/50
Flexural Modulus - Secant	2000	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	4.0	kJ/m <sup>2</sup>	
23°C	20	kJ/m <sup>2</sup>	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: [sales@su-jiao.com](mailto:sales@su-jiao.com)

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

