

LG ABS HF380

Acrylonitrile Butadiene Styrene

LG Chem Ltd.

Message:

LG ABS HF380 is an Acrylonitrile Butadiene Styrene (ABS) material. It is available in Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of LG ABS HF380 are:

Flame Rated

High Flow

Typical applications include:

Consumer Goods

Electrical/Electronic Applications

General Information			
UL YellowCard	E248280-462761	E67171-248362	
Features	High Flow		
Uses	Electrical/Electronic Applications		
	Toys		
Processing Method	Injection Molding		
Multi-Point Data	Specific Heat vs. Temperature (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	43	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 to 0.70	%	ASTM D955
Dimensional Stability	0.0	%	ASTM D1042
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹ (3.20 mm)	2150	MPa	ASTM D638
Tensile Strength ² (Yield, 3.20 mm)	42.2	MPa	ASTM D638
Tensile Elongation ³ (Break, 3.20 mm)	30	%	ASTM D638
Flexural Modulus ⁴ (3.20 mm)	2400	MPa	ASTM D790
Flexural Strength ⁵ (3.20 mm)	68.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm	120	J/m	
-30°C, 6.40 mm	120	J/m	
23°C, 3.20 mm	250	J/m	
23°C, 6.40 mm	250	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648

0.45 MPa, Unannealed, 6.40 mm	89.0	°C	
1.8 MPa, Unannealed, 6.40 mm	84.0	°C	
Vicat Softening Temperature	94.0	°C	ASTM D1525 ⁶
RTI Elec			UL 746
1.50 mm	60.0	°C	
3.00 mm	60.0	°C	
RTI Imp			UL 746
1.50 mm	60.0	°C	
3.00 mm	60.0	°C	
RTI Str			UL 746
1.50 mm	60.0	°C	
3.00 mm	60.0	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+13	ohms·cm	ASTM D257
Dielectric Strength	34	kV/mm	ASTM D149
Arc Resistance	PLC 6		ASTM D495
Comparative Tracking Index (CTI)	PLC 1		UL 746
High Amp Arc Ignition (HAI)			UL 746
1.50 mm	PLC 0		
3.00 mm	PLC 0		
High Voltage Arc Tracking Rate (HVTR)	PLC 1		UL 746
Hot-wire Ignition (HWI)			UL 746
1.50 mm	PLC 3		
3.00 mm	PLC 3		
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm, ALL	HB		
3.00 mm, ALL	HB		
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	180 to 200	°C	
Middle Temperature	190 to 210	°C	
Front Temperature	200 to 220	°C	
Nozzle Temperature	200 to 230	°C	
Processing (Melt) Temp	210 to 240	°C	
Mold Temperature	40.0 to 70.0	°C	
Back Pressure	29.4 to 58.8	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	1.0 mm/min		
2.	50 mm/min		

3.	50 mm/min
4.	15 mm/min
5.	15 mm/min
6.	Rate A (50°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

