

Durethan® BKV 30 EF 000000

Polyamide 6

LANXESS GmbH

Message:

PA 6, 30 % glass fibers, injection molding, improved flowability

General Information				
UL YellowCard		E245249-473588		
Filler / Reinforcement		Glass fiber reinforced material, 30% filler by weight		
Features		Good liquidity		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.35	--	g/cm ³	ISO 1183
Apparent Density	0.60	--	g/cm ³	ISO 60
Molding Shrinkage				ISO 2577
Vertical flow direction: 260°C, 2.00mm ¹	0.58	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.14	--	%	ISO 2577
Flow direction: 260°C, 2.00mm ³	0.23	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.050	--	%	ISO 2577
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	190	--	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				
23°C	9020	5530	MPa	ASTM D638
23°C	9300	5700	MPa	ISO 527-2/1
Tensile Strength				
Fracture, 23°C	174	97.2	MPa	ASTM D638
Fracture, 23°C	180	100	MPa	ISO 527-2/5
Tensile Elongation				
Fracture, 23°C	3.2	5.6	%	ASTM D638
Fracture, 23°C	3.0	6.0	%	ISO 527-2/5
Flexural Modulus				
23°C	7800	5100	MPa	ASTM D790
23°C ⁵	8400	6000	MPa	ISO 178/A
Flexural Strength				
23°C	270	170	MPa	ASTM D790

3.5% strain, 23°C	250	155	MPa	ISO 178/A
23°C ⁶	265	180	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	4.0	5.3	%	ISO 178/A
ISO Shortname	PA 6, GR, 10-090, GF30	--		ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	10	10	kJ/m ²	ISO 179/1eA
23°C	12	18	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	50	45	kJ/m ²	ISO 179/1eU
23°C	65	85	kJ/m ²	ISO 179/1eU
Notched Izod Impact				ISO 180/1A
-30°C	10	10	kJ/m ²	ISO 180/1A
23°C	10	15	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-40°C	45	40	kJ/m ²	ISO 180/1U
23°C	60	80	kJ/m ²	ISO 180/1U
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	2.80	--	J	ISO 6603-2
23°C	2.90	--	J	ISO 6603-2
Multi-Axial Instrumented Impact Peak Force				ISO 6603-2
-30°C	797	--	N	ISO 6603-2
23°C	813	--	N	ISO 6603-2
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	220	--	°C	ISO 75-2/B
1.8 MPa, not annealed	210	--	°C	ISO 75-2/A
8.0 MPa, not annealed	150	--	°C	ISO 75-2/C
Vicat Softening Temperature	210	--	°C	ISO 306/B120
Melting Temperature ⁸	220	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	2.0E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	1.0E-4	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method

Comparative Tracking Index (Solution A)	550	--	V	IEC 60112
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	250 - 290		°C	
Mold Temperature	80.0 - 120		°C	
NOTE				
1.	60x60x2mm, 80°C MT, 600 bar			
2.	60x60x2mm			
3.	60x60x2mm, 80°C MT, 600 bar			
4.	60x60x2mm			
5.	2.0 mm/min			
6.	2.0 mm/min			
7.	2 mm/min			
8.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

